



Add:2-C03Room,2 Build, No. 1588 of Huhang Road , Shanghai City, China.

Add thickener and stir at high speed to make color paste, print → dry → set (cotton: 160 °C x 50 s; polyester/cotton: 170-180 °C x 50 s).

Note

The specific amount of waterproofing agent should be adjusted according to the fabric variety and processing technology.

Package

SILIT-PR-3917G is available in 120kg plastic drums.

Storage and shelf-life

This product is a thermally reactive resin, and should be stored away from direct sunlight and away from the heating element. Store in a cool and ventilated warehouse (5~35) with a storage period of one year. After opening the lid, it should be used up as soon as possible. Past this date, **SHANGHAIVANABIOTECH** no longer guarantees that the product meets the sales specifications.